

MASTERKURE® N-Seal-W

Modified acrylic, water-based curing and sealing compound for concrete

DESCRIPTION:

MASTERKURE® N-Seal-W curing and sealing compound is a modified acrylic, water-based liquid polymer product for new or existing concrete surfaces. It can be applied vertically or horizontally, indoors or outdoors, to smooth or textured concrete. MASTERKURE N-Seal-W compound is recommended for use on concrete floors as classified in ACI Guide 302.1R, Table 2.1. When a second coat is applied, the material can offer some concrete sealing characteristics.

RECOMMENDED FOR:

- Curing freshly placed and finished concrete floors as classified in ACI Guide 302.1R, Table 2.1
- Use as an economical protective sealer for concrete, precast, paving stones, exposed aggregates and terrazzo
- Use when removal of curing compound is not desired or required

FEATURES/BENEFITS:

- Proper curing of concrete ensures increased durability
- Enhances the concrete surface with a light patina coating
- Reduces surface absorption of concrete
- Designed to make surfaces easier to clean and maintain
- Complies with ASTM C 309, Type 1, Class A and Class B
- Complies with AASHTO M-148

PACKAGING:

MASTERKURE N-Seal-W compound is packaged in 5 gallon (18.9 liter) pails, and 55 gallon (208 liter) drums.

SHELF LIFE:

Shelf life is approximately one year if stored in original, unopened containers and stored between 40 to 85 °F (4.4 to 29.4 °C). Keep from freezing.

ESTIMATING:

First Coat

One gallon will cover approximately 200 to 400 ft² (4.9 to 9.8 m²/liter), depending on texture and porosity of surface.

Second Coat

One gallon will cover approximately 400 to 600 ft² (9.8 to 14.7 m²/liter), depending on texture and porosity of surface.

PERFORMANCE DATA¹:

(Field Properties May Vary)

Volatile Organic Compounds	1.22 lb/gal (146 g/L)
Flash Point (Setaflash Closed Cup)	200 °F (93 °C)
Color	Opaque

¹ Properties are typical and descriptive of the product and may be used as a guide for determining suitability of particular applications.

INSTALLATION:

Read and understand data sheet and installation instructions completely before beginning installation.

Surface Preparation

Freshly placed concrete surface must be properly finished. First coat should be applied uniformly as soon as possible after final finishing. Surface is application ready when damp but not wet, and can no longer be marred by foot traffic.

Existing concrete surface should be thoroughly repaired and cleaned prior to application. Surface must be clean, dry, and free of loose materials, oil, grease, sealers, and all other surface contaminants that may inhibit proper bonding of material.

Application

Thoroughly mix material in original container prior to application.

Apply material to form a continuous, uniform film by sprayer, roller, or other approved application equipment.

For sealing new or existing concrete, two coats are required.

Drying Time

Drying time is approximately 3 hours at 70 °F (21 °C), with relative humidity at 50%. Material will take longer to dry at either higher humidity and/or lower temperatures.

Based upon temperatures of 65 to 85 °F (18 to 29 °C):

- Light foot traffic, or between coats 4 hours
- Normal traffic Overnight
- Maximum hardness 7 days

Clean Up

Clean tools immediately after use with water.

LIMITATIONS:

- For professional use only. Not intended for sale or use by the general public.
- Keep from freezing.
- Do not apply when surfaces or ambient temperatures are below 40 °F (5 °C).
- Do not subject to rain or water until material dries hard (48 hours or longer, depending on temperature and relative humidity).
- Not intended for surfaces to receive concrete overlays or additional toppings, coatings or sealers, unless plans are made to mechanically remove.
- Not recommended as a release agent.
- Do not use in areas that require resistance to solvents such as gasoline, diesel fuel, or paint thinners.
- Do not apply to the interfacing of channels to be caulked. Mask channels to minimize adhesion problems.
- Can be applied to natural or colored concrete, but mottling or ambering may occur.
- Prolonged exposure to moisture may result in a temporary opaque condition that clears upon drying.
- May rubber burn (tire marks) when subjected to fork lift or other wheeled traffic.
- May highlight features and imperfections of the concrete surface.

SAFETY PRECAUTIONS:

MASTERKURE N-Seal-W curing and sealing compound contains propylene glycol phenol ether.

Risks

May cause eye, skin and respiratory irritation. INTENTIONAL MISUSE BY DELIBERATELY INHALING THE CONTENTS MAY BE HARMFUL OR FATAL.

Precautions

KEEP OUT OF THE REACH OF CHILDREN. Avoid contact with eyes, skin and clothing. Avoid breathing vapors. Use only with adequate ventilation. DO NOT take internally. Wash thoroughly after handling. Use impervious gloves, eye protection and if the TLV is exceeded or product is used in poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state and local regulations. Keep container closed when not in use.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists, or any breathing difficulty occurs, or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheets (MSDS) for further information.

Proposition 65

This product does not knowingly contain materials as listed by the State of California as known to cause cancer or birth defects or other reproductive harm.

Volatile Organic Compound (VOC) Content

1.22 lb/gal (146 g/L) less water and exempt solvents.

For medical emergencies only,
call ChemTrec: (800) 424-9300

RELATED BULLETINS:

MSDS - MASTERKURE N-Seal-W compound

For additional information, contact your local Master Builders representative.

Master Builders, Inc. United States

23700 Chagrin Boulevard
Cleveland, Ohio 44122-5554
(800) MBT-9990
Fax (216) 831-6910

Canada

3637 Weston Road
Toronto, Ontario M9L 1W1
(800) 387-5862
Fax (416) 741-7925

Mexico

Blvd. M. Avila Camacho 80, 3er Piso
53390 Naucalpan, México
011-525-557-5544
Fax: 011-525-395-7903